


Technical Data Sheet

StoColor Lastic

Facade paint on dispersion base, cold-elastic



Characteristics

Application

- exterior
- as intermediate and top coat in the Sto crack repair system for cracks up to max. 1.0 mm
- a double material application of StoColor Lastic is suitable for crack widths of up to max. 1.2 mm (class A 3 in accordance with EN 1062-7)
- a double coat is generally required to achieve optimum crack-bridging
- not suitable for horizontal or sloping surfaces
- do not apply onto lime-containing substrates and surfaces of mortar groups PI (DIN 18550) and CS1 (in accordance with EN998-1) with strengths less than 1 N/mm²
- do not use on surfaces that are contaminated with plasticisers and paraffin (e.g. from not fully removed strippers)

Properties

- special, UV-curing, highly elastic dispersion paint
- very high resistance to soiling for such a highly elastic facade paint
- excellent hiding power
- very highly water-repellent
- water vapour permeable
- cold-elastic

Appearance

- silk matt

Information/notes

- with film conservation to ward off algae and/or fungal attack

Technical data

Criterion	Standard / test regulation	Value/ Unit	Notes
Density	EN ISO 2811	1.3 - 1.5 g/cm ³	
Diffusion-equivalent air layer thickness	EN ISO 7783-2	1.6 m	V3 low
Water permeability rate w	EN 1062 -3	< 0.1 kg/(m ² *h ^{0.5})	W3 low
Water vapour diffusion resistance factor μ	EN ISO 7783-2	3,900	average value
Gloss	EN 1062-1	matt	G3
Dry layer thickness	EN 1062-1	410 μm	E5 > 400
Grain size	EN 1062-1	< 100 μm	S1 fine

The characteristic values stated are average values or approx. values. We use natural raw materials in our products, which means that the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended purpose.

Technical Data Sheet

StoColor Lastic

Substrate

Requirements The substrate must be firm, dry, clean, and load-bearing, as well as free from sinter layers, efflorescence and release agents. Damp or not fully cured substrates can lead to defects in subsequent coats, such as blistering or cracks.

Preparations Check existing coatings for their load-bearing capacity. Remove any non load-bearing or structurally weak coatings.

Application

Application temperature Lowest temperature of substrate/air: +5°C
Highest temperature of substrate/air: +30°C

Material preparation Intermediate coating diluted with max. 2% water.
Top coat undiluted.

Use as little water as possible to achieve application consistency. Stir well before application. For machine application the amount of water added depends on the requirement of the respective machine/pump. As a rule, strong colour shades need less water to achieve the optimum application consistency. Too much thinning of the material will make application more difficult and will result in poorer characteristics (e.g. hiding power, colour shade).

Consumption	Type of application	Approx. consumption		
	per paint coat	0.35 - 0.45	l/m ²	
	for 2 coats	0.70 - 0.90	l/m ²	

The consumption of the material depends on the application method, substrate and consistency, amongst other factors. The stated consumption rate is only to be used as a guide. Where required, precise consumption values should be established on the respective project.

Coating procedure Substrate coating:
Depends on the type and condition of the substrate.

Intermediate coating:
StoColor Lastic

Top coat:
StoColor Lastic

Application Painting, rollers
Simple, supple application.

Drying, curing, reworking time When there is high humidity and/or low temperatures, the drying process will be delayed accordingly.

During unfavourable weather conditions it is imperative that suitable protective measures (e.g. protection against rain) be applied to the work in progress and freshly completed facades.

Technical Data Sheet

StoColor Lastic

At +20°C temperature (air and substrate) and 65% relative air humidity, the next coat can be applied after approx. 12 hours.

Cleaning the tools Clean tools with water immediately after use.

Delivery

Colour shade White, tintable in accordance with the StoColor System
Colour stability:
 The effects of the weather, humidity, UV irradiation and deposits can lead to changes in the coating surface over time. This can result in colour changes. This is a dynamic process which varies according to climate conditions and the degree of exposure. The respective current national regulations, data sheets, etc. apply.

Filler break:
 When coated surfaces are exposed to mechanical stress it is possible that, due to the natural calibration grains used for darker, more intense colour shades, the areas of impact change to a lighter colour. This does not affect the quality and functionality of the product.

Colour accuracy:
 It is not possible to give any warranty for uniform colour accuracy and freedom from stains due to chemical and/or physical curing processes and fluctuations in the weather and different substrate conditions, especially in the case of:
 a) uneven absorption behaviour of the substrate
 b) different substrate moistures over the entire the surface
 c) partially very different alkalinity/substances from the substrate
 d) direct solar radiation with sharply delineated shadowing on the freshly applied coating.

Emulsifier washouts:
 Due to conditions which delay drying, surface effects (streaking) can occur on coatings which are not yet fully-dried during initial stages of weathering caused by dew, mist, water spray or rain because of water-soluble additives. Depending on the colour intensity, this effect can occur to varying degrees. This does not constitute an impairment of product quality. These effects are normally removed automatically on further weathering.

Tintable It can be tinted by the user with StoColor Tint or with max. 1% StoTint Aqua.

Special options possible The product is equipped at the factory with adapted film conservation against algae and fungal attack, it is not possible to add agents. A preventive and delaying effect is achieved. However, it is not possible to guarantee that there will be no algae and/or fungal attack in the long term.

Packaging Pail

Storage

Storage conditions Store tightly sealed in frost-free conditions. Protect against heat and direct sunlight.

Technical Data Sheet

StoColor Lastic

Storage life The quality of the original package is guaranteed until stock by date. The stock by date can be deduced from the batch number of the package.
 Batch number explanation:
 Number 1 = the last number of year, numbers 2 + 3 = a week
 I.e.: 1450013223 – stock date until the 45th week of the year 2011

Certificates / approvals

Identification

Product group Facade paint

Composition In accordance with VdL (German Paint and Printing Ink Association) guideline: Construction coating materials for buildings, Polymer dispersion, Titanium dioxide, Calcium carbonate, Talcum, Water, Glycol ether, Aliphatics, Additive, Preservative

Security This product is a hazardous material.
 Please observe safety data sheet

Special information

The information or data serves to ensure the product's intended purpose or its suitability for use and is based on our findings and experience. Nevertheless, users are responsible for establishing the suitability of the product for its intended use. Applications other than those explicitly mentioned in this technical data sheet are only permissible after prior consultation with Sto AG. Where no approval is given, such applications are at the risk of the user. This applies in particular when the product is used in combination with other products. When a new technical data sheet is published, all previous technical data sheets are no longer valid. The latest version is available on the Internet at www.sto.com.

Sto AG
 Ehrenbachstr. 1
 D - 79780 Stühlingen
 Phone: +49 7744 57-0
 Fax: +49 7744 57-2178
 Infoservice.export@sto.eu.com
www.sto.com