

Technical data sheet

StoLook Wax

Transparent protective wax



Characteristics

Areas of application

- interior
- as a protective coating for StoCalce Marmorino, StoCalce Veneziano, and StoCalce Fondo surfaces
- as finishing coat with StoLook Effect Powder
- do not use in splash zones

Properties

- protects the surface
- resistant to mechanical stress
- protects against early soiling

Appearance

- enhances gloss and depth effect

Technical data

Criterion	Standard / test regulation	Value/ Unit	Notes
-----------	----------------------------	-------------	-------

The characteristic values stated are average values or approx. values. We use natural raw materials in our products, which means that the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

Substrate

Requirements

The substrate must be firm, dry, clean, and load-bearing.

Application

Application temperature

Lowest temperature of substrate/air: +5 °C

Technical data sheet

StoLook Wax

Consumption	Type of application	Approx. consumption	
	per application cycle	0.05	l/m ²

Material consumption depends on, among other factors, the application, substrate and consistency. The stated consumption values are only to be used as a guide. If required, precise consumption values should be determined on the basis of the specific project.

Application	apply a thin and uniform wax layer and polish it using a cloth or an abrasion-free spatula
--------------------	--

Drying, curing, ready for next coat	Only apply wax protective coatings after approx. 4-8 days of drying. Drying time depends on the surface technique employed. Applying the wax too early can lead to discolouration.
--	--

Cleaning the tools	Clean tools with water immediately after use.
---------------------------	---

Indications, recommendations, special information, miscellaneous	Excessive amounts of wax or non-uniform application can lead to whitening and fogging. The waxed surface can be cleaned with a damp cloth or commercially-available soap or washing-up liquid. Do not use aggressive cleaning agents, e.g. scouring agents, descalers, and sharp-edged cleaning tools. When reworking waxed surfaces, make sure to remove the wax layer before applying a new layer.
---	--

Delivery

Colour shade	milky white, tintable with StoTint Aqua
---------------------	---

Packaging	tin
------------------	-----

Storage

Storage conditions	Store tightly sealed in frost-free conditions.
---------------------------	--

Storage life	The quality of the original package is guaranteed until stock by date. The batch number of the package indicates the storage life.
---------------------	--

Technical data sheet

StoLook Wax

Batch number explanation:

number 1 = the last number of year, numbers 2 + 3 = a week

e.g. 5450013223 – storage life until the week 45 of the year 2015

Certificates/approvals

Identification

Product group	Wax
---------------	-----

Safety	Please observe safety data sheet
--------	----------------------------------

Special notes

The information or data in this technical data sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Nevertheless, users are responsible for establishing the suitability of the product for its intended use.

Applications other than those explicitly mentioned in this technical data sheet are only permissible after prior consultation. Where no approval is given, such applications are at the risk of the user. This applies particularly to combinations with other products.

When a new technical data sheet is published, all previous technical data sheets are no longer valid. The latest version is available on the Internet.

Technical data sheet

StoLook Wax

Sto SE & Co. KGaA

Ehrenbachstr. 1

D - 79780 Stühlingen

Phone: +49 7744 57-0

Fax: +49 7744 57-2178

Infoservice.export@sto.com

www.sto.com